



MATERIAL COMPARISON

RULON[®] FLUOROPOLYMERS

Grade Color	AR Maroon	LR Maroon	J Gold	641 White	142/142S/242 Turquoise	488 Dull Turquoise	W2 Black	1337 Tan	XL Black	1439 White	945 Black
Max Load	6.9	6.9	5.2	6.9	6.9	6.9	6.9	6.9	8.3	6.9	6.9
"P" MPa (psi)	(1,000)	(1,000)	(750)	(1,000)	(1,000)	(1,000)	(1,000)	(1,000)	(1,200)	(1,000)	(1,000)
Max Speed	2	2	2	2	2	2	2	2	2	2	2
"V" m/s (fpm)	(400)	(400)	(400)	(400)	(400)	(400)	(400)	(400)	(400)	(400)	(400)
Max "PV" MPa * m/s	0.35	0.35	0.26	0.35	0.35	0.35	0.35	0.35	0.35	0.35	0.35
(psi-fpm)	(10,000)	(10,000)	(7,500)	(10,000)	(10,000)	(10,000)	(10,000)	(10,000)	(10,000)	(10,000)	(10,000)
Rb 25 & higher			X	Х		X	×	×	Х	Х	Х
Rc 35 & higher	Х	×			X						
Aluminum			×						×		
FDA compliant				Х				×		×	
Steam	Х	×		Х	Х	×	×	×	×	×	Х
Wet	×	×		Х	×	Х	×	X	Х	Х	×
Dry	×	×	Х	Х	×	Х	×	X	Х	Х	×
Vacuum	Х	×	×	Х	×	×			×	×	
Coefficient of friction	4	4	1	1	2	3	2	2	1	3	2
Creep resistance	3	4	3	4	5	4	4	3	4	4	4
Insulative properties	Yes	Yes	Yes	Yes	No	Yes	No	Yes	Yes	Yes	No

• The list above is only a partial list of the available Rulon[®] grades (formulations).

• PV data may be exceeded based on specific application requirements. Ask to speak to an Omniseal Solutions™ Engineer.

• Ratings above are relative within the Rulon® family ONLY.

• For Rulon® materials, the coefficient of friction decreases with increasing load, and wear decreases with increasing surface hardness.

• For PTFE based materials, wear in steam and wet environments is higher than in dry environments. Omniseal Solutions™ offers enhanced Rulon[®] grades, which minimize this effect.

Most Rulon[®] solutions have excellent chemical compatibility. Data is available upon request.

