

MATERIAL DATASHEET

Meldin® 4320

Features: Black, outstanding wear resistance, recommended for washers

Benefits: Excellent fatigue resistance and low creep

Working Temperature Range: from cryogenic to +270°C [+518°F]

Properties	Test Methods	Typical Values	Units
PHYSICAL			
Specific Gravity	ASTM D792	1.51	--
Water Absorption-RT, 24hr	ASTM D570	0.17	%
MECHANICAL			
Tensile Strength – RT / 235°C	ASTM D638	108 [15,600] / 50 [7,200]	MPa [psi]
Elongation-RT	ASTM D638	2.4	%
Tensile Modulus-RT	ASTM D638	7.2 / [10.4]	GPa [psi x 10 ⁵]
Compressive Strength – RT / 235°C	ASTM D695	129 [18,700] / 71 [10,300]	MPa [psi]
Compressive Modulus-RT	ASTM D695	5.6 / [8.1]	GPa [psi x 10 ⁵]
Flexural strength – RT / 235°C	ASTM D790	173 [25,100] / 67 [11,200]	MPa [psi]
Flexural Modulus-RT	ASTM D790	8.3 / [12]	GPa [psi x 10 ⁵]
THERMAL			
Melting point	ASTM D3418	371 [700]	°C [°F]
Glass Transition Temperature	ASTM D3418	280 [536]	°C [°F]
Linear Coefficient of Thermal Expansion along flow, <Tg / >Tg	ASTM E831	NA	m/m/°C [in/in/°F] x 10 ⁻⁵
Linear Coefficient of Thermal Expansion average, <Tg / >Tg	ASTM E831	NA	m/m/°C [in/in/°F] x 10 ⁻⁵
Thermal Conductivity	ASTM F433	NA	GPa [psi x 10 ⁵]
Heat deflection temperature	ASTM D648	NA	°C [°F]
ELECTRICAL			
Dielectric Strength (2.5 mm thick)	ASTM D149	NA	kV/m [V/mil]
Dielectric Constant-RT, 1kHz)	ASTM D150	NA	-
Volume Resistivity-RT	ASTM D257	NA	Ohm cm

The table above represents typical values, intended for reference only. They should NOT be used as a basis for design specifications or quality control.

Meldin® is a registered trademark. © 2022 Omniseal Solutions™